

## TEST REPORT

**CLIENT:**

Company:	Pro Syn-Turf, Inc.	Report Number:	79410-01
Address:	300 Colonial Center Pkwy, Unit 600	Lab Test Number:	3169-2444
	Roswell, GA 30076	Test Completion Date:	1/16/2020
		Report Date:	1/18/2020
		Page:	1 of 1

**TEST MATERIAL:**

Material Type:	Synthetic Turf			Date Received:	1/13/2020
Material Condition:	EXCELLENT:	XXX	GOOD:	POOR:	REJECTED:
Turf Identification:	Putt Series				
Infill:	None				

**TESTING METHODS REQUESTED:**

<i>Testing Services Inc. was instructed by the client to test for the following...</i>			
Standard:	ASTM D2859	Test Method:	Standard Test Method for Ignition Characteristics of Finished Textile Pile Yarn Floorcoverings

**SAMPLING PLAN:**

Sampling Date:	1/13/2020
<ul style="list-style-type: none"> <li>• Specimen sampling is performed in the sampling department at TSI.</li> <li>• The sampling size of specimens is determined by the test method requirements.</li> <li>• In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager.</li> <li>• All samples are subjected to the outside environmental conditions of temperature and relative humidity.</li> <li>• Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested</li> </ul>	

**DEVIATION FROM TEST METHOD:**

<b>State reason for any Deviation from, Additions to, or Exclusions From Test Method.</b>
Specimens were not exposed to air circulating oven.

**TEST SCOPE:**

This test method provides a method of determining the flammability characteristics of textile products when exposed to an ignition source in a laboratory environment. Eight specimens were taken from the sample lot, 230mm X 230mm, and preconditioned in an air circulating oven @ 150°C for 2 hours. After removal from the oven, the specimens are placed into a desiccator for 1 hour prior to performing the test. Each specimen was then placed into the test chamber floor with the pile surface up and a steel frame, 230mm X 230mm with 200mm diameter hole, placed on top of the specimen. A methenamine tablet was placed centrally onto the pile surface. The pill was ignited using a lighted match, with the ignition flame and propagated flame allowed to self-extinguish.

**CRITERIA:**

The specimen passes, if the charred portion of the test specimen, did not extend to within 25mm (1") of the diameter hole of the steel frame. The U.S. Consumer Product Safety Commission requires that at least seven of the eight specimens pass the test for acceptance as meeting the standard.

**TEST SUMMARY:**

TEST METHOD	TEST DESCRIPTION	TEST RESULT	
ASTM D2859-16	Ignition Characteristics of Textile Floor Coverings (Pill Test)	8 out of 8 Pass	Passes, U.S. CPSC 16CFR 1630 (FF1-70), Carpets & Rugs

**Uncertainty:**

We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available.

TSI can only ensure the test results for the specific items tested.

Unless otherwise noted in the deviations sections of this report, all tests are performed in compliance with stated test method.

Test Report Approval:

Erle Miles, III, Lab Director Testing Services (TSI) LLC

TSI Accreditation: Our laboratory is accredited by the US Dept. of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0. TSI is a certified independent testing laboratory by the Synthetic Turf Council



**100108-0**